

LOCTITE[®] EA 210214

Known as Hysol 210214
October 2014

PRODUCT DESCRIPTION

LOCTITE[®] EA 210214 provides the following product characteristics:

Technology	Epoxy
Chemical Type	Epoxy
Appearance (uncured)	Light grey liquid ^{LMS}
Appearance (cured)	Light grey solid ^{LMS}
Fluorescence	Positive under UV light
Components	One component - requires no mixing
Cure	Heat cure
Cure Benefit	Production - high speed curing
Application	Assembly of disposable medical devices.
Key Substrates	Stainless steel and Plastics

LOCTITE[®] EA 210214 is suitable for a wide range of applications that require fast cure, excellent environmental resistance and high adhesion. The product cures rapidly when exposed to temperatures as low as 100 °C and achieves excellent adhesion to plastics, metals and glass. LOCTITE[®] EA 210214 was specifically designed for bonding stainless steel cannulae into hubs, syringes and lancets for needle assemblies. Suitable for use in the assembly of **disposable medical devices**.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.38
Flash Point - See SDS	
Viscosity, Brookfield SSA - RVT, 25 °C, mPa·s (cP):	
Spindle 14, speed 20 rpm,	22,000 to 28,000 ^{LMS}

TYPICAL CURING PERFORMANCE

Cure Schedule

Typical cure times were estimated as >99% conversion using differential scanning calorimetry:

- @ 100 °C, 25 minutes
- @ 125 °C, 24 minutes
- @ 150 °C, 17 minutes

TYPICAL PROPERTIES OF CURED MATERIAL

Cured for 30 minutes @ 125 °C.

Physical Properties:

Coefficient of Thermal Expansion, ISO 11359-2, K ⁻¹ :	
Pre Tg (Alpha 1)	52×10 ⁻⁶
Post Tg (Alpha 2)	172×10 ⁻⁶
Glass Transition Temperature, ASTM E 228, °C	74
Shore Hardness, ISO 868, Durometer D	≥75 ^{LMS}
Linear Shrinkage, ASTM D 792, %	1.2
Water Absorption, ISO 62, %:	
2 hours in boiling water	1.6
7 days in water @ 22 °C	0.37
Elongation, at break, ISO 527-3, %	1.1
Tensile Strength, ISO 527-3	N/mm ² 38 (psi) (5,540)
Tensile Modulus, ISO 527-3	N/mm ² 3,902 (psi) (566,000)

TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

Cured for 30 minutes @ 120 °C.

Lap Shear Strength, ISO 4587:

Aluminum (etched):	
0.125 mm gap	N/mm ² ≥13.8 ^{LMS} (psi) (≥2,000)

Cured for 30 minutes @ 100 °C.

Needle Pullout Strength:

Material	22 Gauge Cannula	27 Gauge Cannula:
ABS	N 227 (lb) (51)	N 142 (lb) (32)
Acrylic	N 254 (lb) (57)	N 147 (lb) (33)
Polycarbonate	N 107 (lb) (24)	N 116 (lb) (26)
Polyethylene	N 13 (lb) (3)	N 53 (lb) (12)
Polyethylene (plasma treated)	N 200 (lb) (45)	N 138 (lb) (31)
Polypropylene	N 27 (lb) (6)	N 36 (lb) (8)
Polypropylene (plasma treated)	N 147 (lb) (33)	N 116 (lb) (26)
Polystyrene	N 222 (lb) (50)	N 133 (lb) (30)
Polyurethane	N 196 (lb) (44)	N 138 (lb) (31)

Cured for 30 minutes @ 125 °C.

Block Shear Strength, ISO 13445:

Acrylic	N/mm ²	4
	(psi)	(580)
G-10 Epoxy	N/mm ²	17
	(psi)	(2,450)
Nylon	N/mm ²	6
	(psi)	(820)
Polybutylene Terephthalate	N/mm ²	11
	(psi)	(1,640)
Polycarbonate	N/mm ²	2
	(psi)	(305)
Aluminum (grit blasted)	N/mm ²	32
	(psi)	(4,580)
Steel (grit blasted)	N/mm ²	45
	(psi)	(6,590)

TYPICAL ENVIRONMENTAL RESISTANCE

Thermal Stability of Needle Assemblies

Aged @ 60°C and tested @ 22 °C

Needle Pullout Strength, % initial strength retained:

Plastic:	4 Weeks	8 Weeks:
Polycarbonate:		
22 Gauge Cannula	190	190
27 Gauge Cannula	110	110
Polypropylene (plasma treated):		
22 Gauge Cannula	120	150
27 Gauge Cannula	105	105
Polystyrene:		
22 Gauge Cannula	100	110
27 Gauge Cannula	100	100

Sterilization Resistance of Needle Assemblies

Sterilized as indicated and tested @ 22 °C

Needle Pullout Strength, % initial strength retained:


Plastic	Gamma	ETO	Autoclave	
	30 kGy	1 cycle	1 cycle	5 cycles
Polycarbonate:				
22 Gauge Cannula	105	100	110	30
27 Gauge Cannula	90	80	100	75
Polypropylene (plasma treated):				
22 Gauge Cannula	90	100	65	35
27 Gauge Cannula	80	70	110	65
Polystyrene:				
22 Gauge Cannula	90	75	N/A	N/A
27 Gauge Cannula	75	80	N/A	N/A

N/A - Not Applicable. The polystyrene was not compatible with the autoclave sterilization process.

Hot Strength

Cured for 30 minutes @ 125 °C. The bonded specimens were tested at the indicated temperature:


Block Shear Strength, ISO 13445, Polycarbonate



Heat Aging

Cured for 30 minutes @ 125 °C. The bonded specimens were conditioned as indicated and tested at 22 °C.

Block Shear Strength, ISO 13445, Polycarbonate



Chemical/Solvent Resistance

Cured for 30 minutes @ 125 °C. The bonded specimens were conditioned as indicated and tested at 22 °C.

Block Shear Strength, ISO 13445, Polycarbonate

Environment	°C	% of initial strength			
		24 h	100 h	500 h	1000 h
95% RH	40	-----	100	90	135
Ambient Water Submersion	22	-----	120	115	165
Isopropanol	22	120	-----	-----	-----
Heptane	22	210	-----	-----	-----

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use:

1. Adhesive must be room temperature just prior to use.
2. Clean and dry surfaces to be bonded.
3. Apply adhesive evenly to both surfaces.
4. Assemble parts and allow to cure at 100 °C for 25 minutes or until completely firm.
5. Refer to cure schedule for alternate cure information.

Loctite Material Specification^{LMS}

LMS dated August 09, 2002. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1